

A Beacon for Gynaecological Cancers Patients: pH-Sensitive Nanomedicine

Pramod Vishwanath Prasad^{1*} and Utkarsh Kr S²

¹Center for Biomedical Research, Population Council, The Rockefeller University, USA

²Patna Medical College and Hospital, Patna University Campus, India

***Corresponding author:** Dr. Pramod Vishwanath Prasad, Center for Biomedical Research, Population Council, The Rockefeller University, 1230 York Avenue, New York, NY 10065, USA, Tel: +12123278743; Fax: +1 2123277678; Email: pkbiochem@yahoo.com

Received Date: December 26, 2020; **Published Date:** January 18, 2020

Abstract

Emergence of various nanoscale drug carrier platforms as Drug Delivery Systems (DDS) has revolutionized the field of medicine. Nonetheless, the side-effects due to non-specific distribution of anticancer therapeutics in normal, healthy tissues remain to be a prime pitfall in curing cancers. Therefore, to achieve a better therapeutic efficacy, the use of a target-specific delivery, combined with a stimuli-responsive nan carrier system, particularly pH-sensitive nanosystems offer an attractive strategy. Targeted drug delivery through pH-sensitive nanosystems offer the potential to enhance the therapeutic index of anticancer agents, either by increasing the drug concentration in tumor cells and/or by decreasing the exposure in normal host tissues. Therefore, nanoscale-based drug delivery through pH-sensitive nanosystems seem to be a boon for treating gynecological cancers (as well as other cancers) without side-effects or with least harm to normal healthy tissues.

Keywords: Gynaecological Cancers; pH-Sensitive Nano medicine; Liposomes; Polymeric Micelles; Dendrimers; Nanogels

Abbreviations: DDS: Drug Delivery Systems; PK: Pharmacokinetics; NP: Nanoparticles.

Introduction

A hope of successful treatment of cancers without side effects has challenged oncologists and onco-scientists since decades. Burgeoning research in nanotechnology and the depth of understanding in gynae-oncological pathophysiology at the cellular and molecular levels have led to the development of different well-tailored nanosized carriers for drug loading and controlled delivery at the targeted site. In recent years, nanosized carriers (nanocarriers) have gained attention as unique drug delivery agents due to following qualities: (i)

they have abilities to incorporate payloads with different solubilities [1], (ii) they improve the *in vivo* pharmacokinetics (PK) of drugs [2], (iii) they enhance bioavailability (i.e., the drug stability and longevity in the blood circulation with or without additional structural modifications) [3], and (iv) they modify the carriers with targeting ligands on their surface for tumor tissue or cell-specific delivery to minimize side-effects on healthy cells/ tissues [4].

Some of the nanocarriers developed till today are liposomes, dendrimers, polymeric nanoparticles (NPs), gold or other metallic NPs, inorganic NPs made of iron oxide, quantum dots etc [5-7]. Few of them possess unique nature of stimuli-responsiveness. Such stimuli-responsive nanocarriers

have emerged as an “intelligent” or “smart” DDS. Thus, these nanocarriers have exhibited myriads of successful applications in comparison with conventional DDS.

The main purpose of developing nanomedicine and nanotherapies is to avoid damage to healthy organs. So, this innovative approach seems to have tremendous potential to improve the effectiveness of nanomedicine to treat clinical tumors with null side effects [8]. There are several nanomaterials which have been found to be responsive to external (viz., light, ultrasound) and internal stimuli (viz., pH, redox potential, temperature), and have been utilized for cancer therapy and simultaneous diagnosis i.e., theranostics [5,9,10]. Among the various stimuli-responsive nanosystems, pH-stimuli mode is regarded as the most general strategy because of solid tumors acidosis. When exposed to weakly acidic tumor microenvironment, drug carrying pH-responsive nanoplatforms can generate physicochemical changes in their structure and surface characteristics, causing drug release or contrast enhancement at a particular pathological site [11,12].

This ease of controlled drug delivery at the desired site, has incepted the preliminary idea of developing pH-sensitive drug delivery nanosystems. Moreover, the pH-responsive NPs are one of the most extensively studied stimuli-responsive nanosystems. This is due to its sensitivities to the changes in pH condition at the tumor or diseased tissue site [13,14].

Generally, pH-responsive nanoparticles are fabricated either using acid-sensitive linkers or ionizable groups [15]. A variety of pH-sensitive nanoparticles have been designed in recent decades and have characteristic functionalities in the molecular structure, where pKa (negative logarithm of the acid dissociation constant) values are close to the tumor interstitial pH. When these nanoparticles reach tumors where the micro environmental pH is slightly acidic, a pH-dependent structural transformation occurs. The acidic environment at the tumor site triggers the protonation of pH-sensitive moieties, thereby disrupting the hydrophilic-hydrophobic equilibrium within the nanoparticle, in turn causing structural transformation and the release of therapeutic cargo loaded inside.

Despite of few problems associated with nanomedicine, pH-sensitive nanoparticle-based DDS remain as a potential strategy for cancer therapy. Some nanoparticle formulations for cancer treatment have been already approved by regulatory agencies. These formulations exert fewer adverse effects than unmodified or bare drugs [16]. Therefore, in the interest of brevity, this review article simply retrospects and compiles only pH-sensitive nanosystems among other internal stimuli-responsive systems. Some of the pH-sensitive nanosystems retrospected here are certainly not yet directly

used for treating gynecological tumors but paves the way for employing them for treating gynecological cancers with some strategic modifications depending on tissue types.

pH-Sensitive Nano-Systems

Generally, physiological pH remains 7.4 (weakly basic) but the subcellular compartments viz., endosomes and lysosomes exhibit remarkably lower pH of about 5-6 or 4-5, respectively. Therefore, significant lower pH in subcellular compartments has been used as a route for delivering anticancer drugs by the pH-stimulated release from endocytosed drug carriers [17]. Since the inception of pH-sensitive NPs, myriads of innovative approaches for cancer treatment have come into light. Past decades have witnessed synthesis and utilization of various pH-responsive nanosystems viz., liposomes, block copolymers, polymeric micelles, polymerosomes, polymer-drug conjugates, dendrimers, nanogels, and multiple core shell complexes etc [18]. These are briefed as follows:

Liposomes

They are phospholipid vesicles consist of one or more concentric lipid bilayers enclosing discrete aqueous spaces. They can entrap both lipophilic and hydrophilic compounds thus employed for delivering diverse range of drugs. Moreover, its large aqueous center and biocompatible lipid exterior permits the delivery of different macromolecules, viz., DNA, proteins and imaging agents [19]. Thus, liposomes are the most common and widely sleuthed nanocarriers for targeted drug delivery due to their flexible physicochemical and biophysical properties [19]. Pegylated liposomal Doxorubicin (DOX: a tumor-specific peptide and chemotherapeutic agent) has been observed to be efficient in breast cancer treatment both as monotherapy and in combination with other chemotherapeutics [20].

In 2016, Silva and colleagues have reported pH-sensitive long-circulating liposomes for selective delivery of DOX into tumor [21]. Karanth and Murthy have extensively analysed previous reports on the cytosolic delivery of the drugs through pH-sensitive liposomes and suggested that pH-sensitive liposomes were more efficient in delivering anti-cancer drugs than conventional and long-circulating liposomes due to their fusogenic property [22]. Recently, a team of investigators have lucidly elaborated the developmental and applicability status of pH-sensitive liposomes in cancer treatment and concluded it very successful as pharmaceutical carriers for intracytoplasmic delivery of antineoplastic drugs [23].

Few investigators have reported pH sensitive coiled coils and their incorporation into the liposome as triggers for the controlled release of encapsulated drugs. From, the drug encapsulated liposome internalization experiments with cancer cells, they revealed the enhanced release and

accumulation of drugs in the acidic lysosomal compartments in comparison with liposomes without coiled coils [24]. In an attempt to develop targeted drug delivery systems with cancerous cell-specificity and controlled release function inside cancer cells, Miyazaki and colleagues have designed hyaluronic acid (HA)-based pH-sensitive polymers as multifunctional polymers.

These polymers exhibited not only pH-sensitivity but also targeting properties to cells expressing CD44 (a cancer cell surface marker). They observed that HA-derivative modified liposomes can be efficiently used for cell-specific intracellular drug delivery [25]. Further research studies on the therapeutic and clinical aspects of pH-sensitive liposomes are needed to enable their commercial utility in gynecological cancer treatment.

Block copolymers

Amphiphilic block copolymers are self-assembled into polymeric micelles (10-100 nm in diameter) in aqueous media. These micelles possess a well-defined hydrophobic core and a hydrophilic corona. Block copolymer micelles can thus significantly improve the solubility of the hydrophobic drug formulated in the core; whereas, the densely packed corona consists of the hydrophilic end of the block copolymer, can protect the micellar system from the RES elimination by reducing the interaction with serum proteins and renal filtration [26]. The pH-sensitive block-copolymers allow for controlled micelle dissociation and triggered drug release in response to the acidic pH of tumor tissue.

The pH-sensitive polymeric micelles assembled from hyperbranched amphiphilic block copolymer loaded with DOX have exhibited remarkable cytotoxicity against HeLa cells in a dose- and time-dependent manner. Thus, proved to be a potential carrier candidate for pH-responsive drug delivery in treating cancer [27]. Moreover, a dual-pH-sensitive micelle loaded with Paclitaxel (PTX, a chemotherapeutic agent) has been also proved to be a potential nano carrier for effective metastatic tumor therapy without significant toxicity [28]. Poly (ethylene glycol) methyl ether acrylate-block poly(L-lysine)-block-poly(L-histidine) triblock co-polypeptides were synthesized for pH-responsive drug delivery. Such nanoparticles were found to be stable at physiological pH (7.4) but were dramatically destabilized in acidic pH due to the presence of pHis blocks [29].

The pH-induced destabilization of the nanoparticle enabled the controlled release of DOX, followed by a dose-dependent cytotoxicity in murine cancer cells. YangZhang et. al. (2012) have reported a series of DOX-loaded pH-responsive poly (ethylene glycol) methyl ether-b-(poly lactic acid-co-poly (β -amino esters)) (MPEG-b-(PLA-co-PAE)) block copolymer

micelles as drug delivery carriers for targeted cancer therapy with sustained release [30]. Investigations carried out by Zhou et. al. (2015) have suggested that the polymeric micelles comprising of polyethylene glycol (PEG) and a polymethacrylamide [PEG-b-PMEA] diblock copolymer could be useful for pH-responsive delivery of poorly soluble anticancer drugs [31].

The pH-sensitive copolymer viz., methoxy poly(ethylene glycol)-b-poly(hydroxypropyl methacrylamide-g- α -tocopheryl succinate-g-histidine) (PTH) forming micelles in aqueous solutions were used for co-delivery of therapeutic agents, DOX and α -TOS (α -tocopheryl succinate) in tumor cells. In this combination therapy, the micelles enabled the rapid release of both Dox and α -TOS when the pH declined from 7.4 to 4.5 in tumor tissues [32]. Mozhi and colleagues have displayed a synergistic antitumor effect of the combination of anticancer drug Docetaxel and the therapeutic peptide [D(KLAKLAK)2] in an MCF-7 cell line using a pH-sensitive copolymer viz., poly(β -amino esters)-poly(ethylene glycol) conjugated with the dual-targeting proapoptotic peptide CGKRK(DKLAKLAK)2.

In which, CGKRK peptide efficiently transported D(KLAKLAK)2 towards mitochondria to trigger mitochondria-dependent apoptosis [33]. Few investigators have reported synthesis of pH-sensitive copolymer through bridging poly (2-methacryloyloxyethyl phosphorylcholine) (PMPC) block and poly (D, L-lactide) (PLA) block by a benzoyl imine linkage (Blink).

These biomimetic micelles (PLA-Blink-PMPC) were prepared as carriers for PTX delivery. Such pH-triggered drug release behaviour in synchronization with tumoral acidic conditions was found to be helpful for improving the utilization of drug and facilitating antitumor efficacy [34]. Furthermore, Wang and colleagues have exhibited antitumor efficiency of DOX-loaded micelles. In which, ortho ester degradation of DOX-loaded, pH-sensitive micelles consisted of triblock copolymer PEG-block-poly(ortho ester urethane)-block-PEG (PEG-POEU-PEG) were found to notably accelerated at pH 5.0 due to its pH sensitivity [35]. This year, few investigators have reported a chemo-photothermo therapy of cancer cells by using gold nanorods (AuNRs)-based pH-sensitive thiol-ended triblock copolymer micelles (PAA-b-PDMAEMAQ-b-PCL-SH), in which AuNRs at polymer was loaded with methotrexate (MTX) as an anticancer drug [36].

Polymeric micelles

They are self-assembling nano-constructs of amphiphilic copolymers and are widely regarded as efficient nano-carriers for myriads of applications, including drug delivery, diagnostic imaging etc. These became feasible because of

their variety of favorable properties viz., biocompatibility, bioavailability, capacity to effectively solubilize myriads of poorly soluble drugs, enhancing release profile of the incorporated pharmaceutical entities, ability to accumulate in the targeted tissue based on the EPR effect and ability to attach various targeting ligands to the micellar surface.

The combination of these approaches have been found to further improve specificity and efficacy of micelle-based drug delivery to promote the development of smart multifunctional micelles [37]. Ko and colleagues have evaluated anti-tumor activity of pH-responsive polymeric micelles made up of methyl ether poly(ethylene glycol) (MPEG)-poly(β -amino ester) block copolymers, by injecting the DOX-loaded polymeric micelles into tumor-bearing mice. These micelles notably suppressed tumor growth and prolonged survival of the tumor-bearing mice, compared with mice treated with free DOX [38].

Giacomelli and coworkers have reported pH-triggered micelles composed of a pH-responsive PDPA [poly(2-diisopropylamino) ethyl methacrylate] inner core and a PEO [poly(ethylene oxide)] outer shell as a promising drug delivery system for the cancer therapy. In which, pH-responsive PDPA core was loaded with PTX [39]. *In vivo* evaluation of DOX-loaded pH-sensitive polymeric micelles made up of poly(L-histidine-co-L-phenylalanine-b-PEG and poly(L-lactic acid)-b-PEG-folate was carried out in multidrug-resistant (MDR) ovarian tumor-xenografted mice.

It was observed that the drug-carrying micelles were exhibiting enhanced intracellular DOX-delivery by circulating for long-time (i.e., enhanced bioavailability) and accumulating at tumor-selective sites. Thus, they exhibited enhanced cytotoxicity to tumor cells only, sparing the normal healthy cells [40]. Wang and colleagues have shown that the PTX loaded pH-responsive Poly(ethylene glycol)-b-poly (D,L-lactide)-b-poly(β -amino ester) [PELA-PBAE] micelles might have the potential utility in the metastatic breast tumor therapy [41].

In another study, the polymeric micelles incorporated with cisplatin were prepared by complexation between cis-dichlorodiammineplatinum(II) (CDDP) and hydrophilic poly (L-glutamic acid)-b-poly (2-methacryloyloxyethyl phosphorylcholine) (PLG-b-PMPC) diblock copolymers. Investigators observed the sustained release of CDDP from the micelles was faster in acidic pH (5.0 - 6.0) than the physiological pH 7.4. Thus, CDDP-loaded polymeric micelles were developed for targeted cancer therapy to reduce the detrimental side effects of cisplatin CDDP [42]. Zhou and coworkers have reported a pH-responsive pentablock copolymer made up of 1,2-distearoyl-sn-glycero-3-phosphoethanolamine-N-[methoxy(polyethylene glycol)]

conjugated poly(β -amino esters) (DSPE-b-PEG-b-PAE-b-PEG-b-DSPE) was able to self-assemble into polymeric micelles. These DOX-loaded polymeric micelles displayed pH-triggered high toxicity to tumor cells and HeLa cell lines whereas the copolymer had negligible cytotoxicity.

Thus, these pH-sensitive micelles have the potential to be used for cancer chemotherapy with controlled release [43]. Das and his team, and Zhou and colleagues have lucidly elaborated the current advances in the development of pH-responsive polymeric micelles/ nanoparticles, their mechanisms of action, applications in chemotherapy, diagnostic imaging, their delivery strategies and provided their future perspectives [44,45]. This is yet to be sleuthed in human cells and gynecological tissues.

It is well understood that, among amino acids, Histidine (His) is an only essential amino acid having imidazole group. The presence of lone-pair electrons on the unsaturated nitrogen of this group confers pH-sensitivity to Histidine. Therefore, poly(Histidine) (pHis) has been extensively used for the fabrication of pH-sensitive drug delivery nanosystems. Uthaman and his team (2018) have reported a variety of pHis-based polymeric micelles for the delivery of DOX [15,29,46-48]. In addition to these, nanocarriers composed of amphiphilic, biocompatible chitosan polymeric micelles were used to deliver Nonsteroidal anti-inflammatory drug (NSAID) Ibuprofen in breast cancer therapy. It was observed to possess potential anti-tumor activity, while avoiding side-effects on normal, healthy tissues [49]. The pH-responsive nanoparticles combining Ibuprofen with chemotherapy agents have provided a novel nanoparticle system for both primary and metastatic tumor treatment [50].

Targeted efficient delivery and therapeutic efficacy of DOX have been found to be significantly increased by using a stepwise pH-responsive nanodrug delivery system [51]. This study has provided a promising strategy for efficient delivery of other antitumor agents. Similarly, some more nanocarriers like polymeric micelles, liposomes and solid NPs have been developed for hydrophobic as well as hydrophilic drugs for effective therapy of cancer [52-56]. Last year, some investigators have revealed the intracellular pH-responsive nanoparticles of hyaluronic acid which can provide insights into the design of potential prodrugs for the cancer therapy [57]. Hydroxyapatite coated iron oxide nanoparticles and pH sensitive Sodium alginate have been developed for controlled release of hydrophobic drugs [58]. Yandan and his colleagues have shown that multifunctional sharp pH-responsive nanoparticles made up of poly(2-(diisopropylamino)ethylmethacrylate) (PDPA) polymer have great potential to serve as a new generation nanomedicine for effective breast cancer treatment [59].

Polyersomes or polymeric vesicles

They are preferably prepared from amphiphilic, biocompatible and biodegradable polymers [60]. They have the potential to be versatile drug delivery systems because of their tunable membrane formulations, stabilities *in vivo*, various physicochemical properties, controlled release mechanisms, targeting abilities, and capacities to encapsulate varieties of drugs etc [61,62]. The pH-sensitive polyersomes have been developed to quickly respond to small changes in the environmental pH of tumor's microenvironment [60,63].

Following pH alteration, the pendant acidic (carboxylic acids/sulfonic acids) or basic groups (amine) undergo protonation or deprotonation. Consequently, the structural transition induces formation/deformation of polymeric vesicles, which confers a higher therapeutic index as a result of the fast release of therapeutics at the target site. However, the major obstacle to the application of pH-sensitive polyersomes is the slow response to the stimulus, resulting in a slow drug release, which eventually induces drug resistance in the adjacent cells. Therefore, polyersomes need to respond quickly as a result of the decreased pH at pathological sites. Thus, pH-responsive polyersomes need to be further designed to carry, deliver, and control the release of therapeutic agents to the tumor tissue by relying on the low pH in the vicinity of tumor tissues [60,63]. Anajafi and Malik (2015) have explicitly elaborated recent developments of polyersomes [60]. Their utilities in treating gynaecological cancers are yet to be sleuthed.

Polymer-drug conjugate

Dendrimers or dendritic molecules are highly branched with a central core, nanosized, symmetric molecules with well-defined, homogenous and monodisperse structure with diameter 2-10 nm. They are classified by their form as polymers, hyperbranched polymers or brush-polymers and also classified by their molecular weight as low or high molecular weight [64,65]. Dendrimer act as a carrier for the delivery of drug to tumor by encapsulation or conjugation. Among polymer-drug conjugates, most widely studied dendrimers to date are non-biodegradable, cationic amine-terminated poly-amidoamine (PAMAM) dendrimers [66]. Drug delivery to tumor site is mostly accomplished through PAMAM, poly (propylene imine) [PPI], and poly(L-lysine) [PLL] dendrimers by either passive or active targeting [64].

Wen and colleagues have explained the multifunctional dendrimer-modified multi-walled carbon nanotubes for targeted and pH-responsive delivery of DOX into various types of cancer cells [67]. In 2018, Zhang and coworkers have reported the development of pH-sensitive multifunctional DOX-conjugated PAMAM dendrimers as a unique platform for targeted cancer chemotherapy [68].

Some other investigators have presented the construction of pH-responsive multifunctional dendrimer-based theranostic nanosystem (in which Gold nanoparticles conjugated with DOX were entrapped in dendrimer) to be utilized for simultaneous chemotherapy and computed tomography (CT) imaging of various types of cancer cells [69].

Dendritic polyester system based on monomers 2,2-bis (hydroxymethyl) propanoic acid attached to DOX or hydroxyl-terminated generation 4 PAMAM in conjugation with PTX through a union with succinic acid have shown great anticancer activity against ovarian cancer cells [65]. However, at present the dendrimers used as drug-carriers do not satisfactorily meet the necessary characteristic of an ideal dendrimer for targeted drug delivery. However, the development and study of new dendrimers drug-carriers continues to be an important tool in the cancer therapy.

Acid-Responsive Polymers

Have provided enhanced endosomal delivery of drugs. In the acidic microenvironment, acid-sensitive linkers have provided tools for targeted intracellular drug release. Hydrazone and cis-aconityl linkers are two types of acid-sensitive linkers which have been commonly used for this purpose. Both are relatively stable at physiological pH and can release the bound drugs only under low pH conditions. The hydrazone linker gets rapidly cleaved under low pH conditions (which occur in endosomes, lysosomes and tumor tissue). Through the hydrazone linker, the drug was found to be released in the acidic tumor microenvironment or in the acidic organelles after cellular uptake by endocytosis [70-75].

Some more sleuthed polymer-drug conjugates containing hydrazone linkages are HPMA-DOX, PEG-DOX [76,77], PEG-epirubicin [78] and PEG-PTXL [79]. Hydrazone linked acid sensitive PEG-based drug delivery in lysosomes was also studied by Zhu et al., 2012 [74]. They found that Gemcitabine (GemC18) in the acid-sensitive micelles was more toxic toward cancer cells than acid-insensitive micelles. There are reports of a pH-sensitive hydrazone bridged and peptide-guided prodrug incorporating DOX for targeted ablation (removal of harmful parts of the body) of cancer cells with least cytotoxicity on normal healthy cells [80].

The pH-sensitive N-(2-hydroxypropyl) methacrylamide-DOX (HPMA-DOX) conjugates bearing an acid-responsive hydrazine linker in their structure have also been widely studied as anticancer drug delivery systems. They have been found to significantly increase therapeutic efficacy in different *in vitro* and *in vivo* cancer models. Liao et al. [57] have reported the synthesis of tumor targeting and pH-responsive nanoparticles for the enhanced delivery of DOX.

The nanoparticles were prepared through the covalent bonding of DOX to hyaluronic acid (HA) backbone by hydrazone linkage. In aqueous solution, hyaluronic acid-hydrazone linkage-doxorubicin (HA-hyd-DOX) could self-assemble into nanoparticles. Active targeting of the nanoparticles was achieved through receptor-mediated binding of HA to CD 44, which are overexpressed in most cancer cells. Studies on polymers that use cis-aconityl linker in designing anticancer drug delivery systems included HPMA-DOX [81], polyamidoamine-DOX [82] and polyamidoamine (PAMAM)-DOX [83].

Furthermore, acid-sensitive cis-aconityl linked Polyethylene glycol-Chitosan (PEG-CS) micelles were found to have a greater Docetaxel loading capacity, less cytotoxicity toward normal cells, enhanced cellular uptake and better accumulation in tumor tissue compared to acid-insensitive PCS micelles (PEG directly linked to CS) [84]. Moreover, the pH-responsive NPs have also been developed by conjugating nanocarriers with some other acid-labile linkages such as orthoester [85,86], imine [87,88], phosphoramidate [89], whose hydrolysis ensured rapid release of the drug at the targeted tumor.

Zwitterionic Polymers

It is well established that the nanoparticles have been designed to demonstrate a pH-dependent change in surface charge. One of the most commonly investigated systems is based on zwitterionic polymers, as they have cationic and anionic groups that control surface charge in response to pH. In acidic pH, these zwitterionic polymers have a positive charge, and in basic pH, they have a negative charge. However, when these zwitterionic polymers are in neutral pH, they are overall neutral with balanced populations of positive and negative components and they become more hydrophobic.

However, upon entering tumor cells, the balance between positive and negative charges alters and thereby causes conformational changes, facilitating drug release in tumor cells. Kang and colleagues have reported the fabrication of tumor microenvironment responsive theragnostic with a pH-dependent fluorescence turn on/off property. The nanoparticles were constructed by encapsulating a photothermal dye (IR 825) in the carbonized zwitterionic polymer. Before accumulating in the tumor site, these nanoparticles displayed quenching of fluorescence due to the hydrophobic interaction with neutral pH and π - π stacking. The slight change in the pH in TME enabled the charge of the nanoparticles to be altered, leading to the release of IR 825 and recovered fluorescence. These types of nanoparticles can simultaneously be used for diagnosis and photothermal therapy [90].

Multiple Core Shell Complexes

The pH-responsive drug encapsulation and release from multiple core-shell nanoparticles become feasible due to the presence of polyelectrolyte multilayers [91]. Huang, et al. [92] first synthesized $Gd_2O_3:Yb^{3+}:Er^{3+}$, a functionalized mesoporous silica nanoparticle core, which was then coated by multi-layers of polyelectrolytes. DOX was then loaded onto the polyelectrolyte shell. The resulting DOX-loaded core-shell nanoparticles exhibited more than 60% DOX release within 72 h at pH 5.2.

In vitro cytotoxicity studies on MCF-7 breast cancer cells showed that DOX-loaded nanoparticles exhibited higher cytotoxicity than the free DOX. Tian, et al. [93] synthesized an azide-terminated diblock copolymer from oligo (ethylene glycol) methyl ether methacrylate (OEGMA), 2-(diisopropylamino) ethyl methacrylate (DPA), and glycidyl methacrylate (GMA). The resulting copolymer was then functionalized with DOTA (Gd) and 4-(prop-2-ynyloxy) benzaldehyde and the resulting copolymers were further co-assembled into mixed micelles.

The presence of GMA moieties inside the cores enabled encapsulation of tetrakis [4-(2-mercaptoethoxy) phenyl] ethylene (TPE-4SH), and thus the resulting micelles were capable of MR and fluorescence dual imaging. Moreover, these micelles were surface-conjugated with pH low insertion peptide (pHLIP), which enabled them for selective targeting toward tumor tissues and *in situ* Camptothecin (a cancer drug) release, confirmed by *in vivo* MR images of tumor-bearing BALB/c nude mice. Ray, et al. (2018) [91] and their collaborators have synthesized a unibody core-shell (UCS) nanoparticle using a polymer platform formed by resorcinol and 1, 3-phenylenediamine monomers.

In this synthesis, Gd^{3+} was first conjugated to the polymer backbone to form the Gd-core, and then DOX was encapsulated within the shell surrounding the Gd-core. Resorcinol was chosen as one of the components in the core. 1,3-phenylenediamine was chosen as the shell unit for its capability for pH-controllable release.

In vitro and *in vivo* studies of UCS-Gd-DOX as an innovative theragnostic nanoparticle showed that the DOX in the shell is effectively and selectively released in tumor acidic environments (pH 5.5). *In vitro* pH-dependant release of DOX after 2 h was found to be <5%, 10%, 55%, 75%, and 80%, at pH 8.0, 7.0, 6.0, 5.0, and 4.0, respectively. Enhanced drug release from pH 7.0 to 6.0 verified the potential of UCS-Gd-DOX for targeted therapy towards malignant tumor tissues. In addition, *in vitro* T1-weighted MR imaging studies also reflected the pH-switchable MR contrast capability of UCS-Gd-DOX.

The pH-responsive design of the UCS nanoparticle not only improved the MRI contrast at the tumor site with respect to other tissue/organs, but also successfully suppressed growth of subcutaneous human cervical cancer in mouse xenograft models. Therefore, theranostic nanoparticles with Gd-conjugation and DOX-doping can be synthesized and further applications of UCS-Gd-DOX in the field of cancer treatment can be anticipated [91].

There are reports of pH-sensitive magnetic nanoparticles sleuthed for targeted anticancer drug delivery. In early years of this decade, a magnetic and pH dually responsive nanocarrier with a multilayer core-shell architecture was constructed. In which, the $\text{Fe}_3\text{O}_4@\text{SiO}_2$ nanoparticles acted as a superparamagnetic core used to target the drug loaded nanocarriers to the pathological site. Meanwhile, the mPEG [α -methoxy poly (ethylene glycol)] and PBLA [poly(benzyl-L-aspartate)] segments served as a pH-sheddable hydrophilic corona and a hydrophobic middle layer used to load the drug DOX via hydrophobic interactions.

This system appeared to be highly promising for the targeted intracellular delivery of hydrophobic chemotherapeutics in cancer therapy [94,95]. In 2017, Karimi and his colleagues have brought in light a pH-sensitive magnetic nanoparticle system for Methotrexate (MTX) targeting of tumor [96]. In another study, Wu and his colleagues have performed *in vitro* evaluation of magnetic nanocomposites ($\text{Fe}_3\text{O}_4@\text{LDH-MTX}$) [in which Fe_3O_4 nanoparticles acted as magnetically responsive carriers and the coating layer of layered double hydroxide (LDH) was used as a storehouse for MTX] as MTX delivery system for targeted anticancer therapy.

They have observed its excellent pH-sensitivity and ~85% of MTX was released within 48h at pH 3.5 via the co-effect of dissolution of LDH layer and ion-exchange. This study has revealed that the $\text{Fe}_3\text{O}_4@\text{LDH-MTX}$ would be a competitive candidate for sustained, controlled release and targeted delivery of MTX because $\text{Fe}_3\text{O}_4@\text{LDH-MTX}$ exhibited high anticancer activity with minimal toxicity to normal cells [97].

In addition to these reports, a pH-responsive nanoplatfrom made up of a yolk-like $\text{Fe}_3\text{O}_4@\text{Gd}_2\text{O}_3$ and functionalized by PEG and folic acid, has been documented to be a potential nanotheranostic for tumor targeted T_1 - T_2 dual-mode Magnetic Resonance Imaging and chemotherapy using Cisplatin and HeLa cells [98]. Last year, pH-sensitive magnetic composite nanoparticle was prepared by double water-in-oil-in-water (W/O/W) emulsion using acetylated β -cyclodextrin as a pH-sensing material and Fe_3O_4 as a component to realize magnetic response. It's *in vitro* evaluation was performed for drug loading and release behaviour [99]. This type of study can be also extended for treating gynecological tumors.

In a review, Lungu and her colleagues have explicitly elucidated the utility of pH responsive core-shell magnetic nanoparticles in diagnosis and treatment of oncological diseases. Those NPs were: magnetite@silicon dioxide ($\text{Fe}_3\text{O}_4@\text{SiO}_2$), Fe_3O_4 @titanium dioxide (TiO_2), beta-thiopropionate-polyethylene glycol (PEG)-modified $\text{Fe}_3\text{O}_4@m\text{SiO}_2$, Fe_3O_4 NPs core coated with SiO_2 with an imidazole group modified PEG-poly-peptide (mPEG-poly-L-Asparagine), polyacrylic acid (PAA) and folic acid coating of the iron oxide NP core, methoxy polyethylene glycol-block-polymethacrylic acid-block-polyglycerol monomethacrylate (MPEG-b-PMAA-b-PGMA) attached by a PGMA block to a Fe_3O_4 core, PEG-modified polyamidoamine (PAMAM) dendrimer shell with Fe_3O_4 core and mesoporous silica coated on Fe_3O_4 , mostly coated with an anticancer drug and used for controlled release of cytostatic drugs into the tumor site by means of pH change [100].

Nanogels

They are three-dimensional, water soluble, cross-linked hydrogel materials in the nanoscale size range with a high loading capacity for guest molecules and act as drug carrier systems [101]. Nanogels are the novel drug delivery systems for both hydrophilic and hydrophobic drugs [102]. There are some anti-tumor drugs viz., Cisplatin, DOX, 5-Fluorouracil, Heparin, Temozolomide etc. used in cancer therapy by incorporation through nanogels. The pH- and temperature-responsive nanogels made up of maleic acid poly-(N-isopropylacrylamide) polymer loaded with DOX have been frequently employed in the cancer treatment, where DOX is delivered at a specific pH and temperature. Chitin-polymerized DOX nanogels have been also used for treatment of breast cancer [103].

Several nanogel formulations used in cancer therapy are listed elsewhere [104]. The pH-sensitive PEGylated nanogel loaded with anti-tumor drug has proved to be a promising nano-sized carrier for anticancer drug delivery systems against the human breast cancer cell line MCF-7 [105]. Bardajee and colleagues have prepared a thermo-/pH-sensitive nanogels comprising salep modified graphene oxide (SMGO) with branched N-isopropylacrylamide (NIPAM) and acrylic acid (AA). Doxorubicin loaded SMGO/P (NIPAM-co-AA) nanogels showed thermo-/pH-dependent drug release and exhibited enhanced toxicity to HeLa cells when compared to the equivalent dose of the free drug [101].

A synergistic combined chemo-radioisotope therapy of cancer using a pH-dependent hybrid nanogel (hydrogel nanoparticle) platform based on the self-assembly of carboxymethyl cellulose and bovine serum albumin is reported for the first time [106]. The pH sensitive polymeric nano-hydrogels attached with ionizable weak acidic or

basic moieties, cationic polymeric polyethylenimine (PEI), polymeric nano-micelles of pH-responsive natural polymers like albumin and gelatin have also been used as drug delivery systems for treating varied cancers [107]. Peng Wei, et al. (2018) have synthesised a pH-sensitive nanogels by using a monomer N-[(2, 2-dimethyl-1,3-dioxolane)methyl] acrylamide (DMDOMA) bearing an acid cleavable acetal group. These seemed to be a promising and conveniently prepared alternative to existing carrier systems for drug delivery [108]. Thus, nanogels seem to be potential candidate in the development of new nanocarriers for anti-cancer drug delivery. So they can be further investigated for treating gynecological cancers.

In all of the aforementioned and other pH-responsive nanosystems reported elsewhere [50,107,109-111], the conventional nano-carriers have been combined with pH-responsive systems that release drug content only under specific acidic pH. Some of the systems discussed here are yet to be investigated for gynaecological cancers. But all of them seem to have tremendous potential for successfully delivering drugs at the targeted gynaecological tumor sites/ tissues, as the case may be. Therefore, it will not be an exaggeration to state that the pH sensitive nanomedicine could turn to be a unique system for treating gynecological cancers (and other cancers, as well), if developed and delivered with utmost care.

Discussion and Conclusion

Despite considerable research in the past decades and plethora of positive results in the preclinical studies, the clinical translation of pH-sensitive nanosystems assisted drug delivery platforms has not progressed incrementally. Some of the facts which appear to be obstacles, seem to hinder this progress are: (i) the difference in pH between normal and tumor tissues are not significant enough for generating the pH-responsiveness. Moreover, pH-sensitive nanoparticles remain non-responsive in the perivascular region because the acidic pH need for responsiveness is found in region far from the blood vessels [29]. (ii) In addition to these, selecting a polymer with a critical pH that matches the desired pH range for its application is a major factor in designing an ideal pH-sensitive system.

Thus, understanding the chemical structure of the polymer's ionizable moieties, and their respective pKa are indispensable for the design and synthesis of appropriate pH-sensitive DDS [112]. Moreover, attempts have been made to alleviate much concerned cytotoxicity of synthesized NPs by conjugating it with PEG or with any of the zwitterionic polybetaines [113-117]. Further studies are still on to nullify its cytotoxicity, if any. Considering all these, it becomes utmost important to understand the nanotechnological advancement in

biomedical applications to date and the challenges that still need to be overcome.

That will allow future research to improve on existing pH-sensitive nanoplatforms and to address the current translational and regulatory limitations. Continued translational success will require coordinated communication and collaboration between experts involved in all stages of pharmaceutical development of pH-sensitive drug delivery nanosystems, including pharmaceutical design, manufacturing, cellular interactions and toxicology, as well as preclinical and clinical evaluation. In all of the aforementioned and other pH-responsive nanosystems reported elsewhere [50,107,115-117], the conventional nano-carriers have been combined with pH-responsive systems that release drug content only under specific acidic pH. Some of the systems discussed here are yet to be investigated for gynaecological cancers. But all of them seem to have tremendous potential for successfully delivering drugs at the targeted gynaecological tumor sites/ tissues, as the case may be. Therefore, it will not be an exaggeration to state that the pH sensitive nanomedicine could turn to be an unique system for treating gynecological cancers (and other cancers, as well), if developed and delivered with utmost care.

References

1. Hu Q, Katti PS, Gu Z (2014) Enzyme-responsive nanomaterials for controlled drug delivery. *Nanoscale* 6(21): 12273-12286.
2. Khadka P, Ro J, Kim H, Kim I, Tae Kim J, et al. (2014) Pharmaceutical particle technologies: an approach to improve drug solubility, dissolution and bioavailability. *Asian J Pharm Sci* 9(6): 304-316.
3. Toh MR, Chiu GNC (2013) Liposomes as sterile preparations and limitations of sterilisation techniques in liposomal manufacturing. *Asian J Pharm Sci* 8(2): 88-95.
4. Fleige E, Quadir MA, Haag R (2012) Stimuli-responsive polymeric nanocarriers for the controlled transport of active compounds: concepts and applications. *Adv Drug Deliv Rev* 64(9): 866-884.
5. Tayo Lemmeul L (2017) Stimuli-responsive nanocarriers for intracellular delivery. *Biophys Rev* 9(6): 931-940.
6. Lehner R, Wang X M, Wolf (2012) Designing switchable nanosystems for medical application. *J Control Release*, 161(2): 307-316.
7. Chen Q, Ke H, Dai Z (2015) Nanoscale theranostics for physical stimulus-responsive cancer therapies.

Biomaterials 73: 214-230.

Pharmacol 6: 286.

8. Camara AL, Figuero Longo JRSJP (2017) pH-Sensitive Nanoparticles for Cancer Therapy: Is this a Real Innovation in Nanomedicine? *Nano Res Appl* 3: 1.
9. Frenkel V (2008) Ultrasound mediated delivery of drugs and genes to solid tumors. *Adv Drug Deliv Rev* 60(10): 1193-1208.
10. Liu YC, Le Ny AL, Schmidt J, Talmon Y, Chmelka BF, Lee CT Jr (2009) Photo-assisted gene delivery using light-responsive cationic vesicles. *Langmuir* 25(10): 5713-5724.
11. Sun X, Zhang G, Wu Z (2018) Nanostructures for pH-sensitive Drug Delivery and Magnetic Resonance Contrast Enhancement Systems. *Curr Med Chem* 25(25): 3036-3057.
12. Sun Hao, Christopher PKabb, Michael BS, Brent SS (2019) Architecture-transformable polymers: Reshaping the future of stimuli-responsive polymers. *Progress in Polymer Science*. 89
13. GaoW, Chan JM, Farokhzad OC (2010) pH-responsive nanoparticles for drug delivery. *Mol Pharm* 7(6):1913-1920.
14. Wang XQ, Zhang Q (2012) pH-sensitive polymeric nanoparticles to improve oral bioavailability of peptide/protein drugs and poorly water-soluble drugs. *Eur J Pharm Biopharm* 82(2): 219-229.
15. John JV, Uthaman S, Augustine R, Chen HY, Park IK et al. (2017) pH/redox dual stimuli-responsive sheddable nanodisks for efficient intracellular tumour triggered drug delivery. *J Mater Chem B* 5(25): 5027-5036.
16. Xin Yanru, Yin Mingming, Zhao L, Meng F, Luo L (2017) Recent progress on nanoparticle-based drug delivery systems for cancer therapy. *Cancer Biol. Med* 14(3): 228-242.
17. Kopansky E, Shamay Y, David A (2011) Peptide-directed HPMA copolymer-doxorubicin conjugates as targeted therapeutics for colorectal cancer. *J Drug Target* 19(10): 933-943.
18. Bazban-SS, Hasani-Sadrabadi MM, Karkhaneh A, Serpooshan V, Jacob KI, et al. (2017) Revisiting structure-property relationship of pH-responsive polymers for drug delivery applications. *J Control Release* 253: 46-63.
19. Sercombe Lisa, Tejaswi Veerati, Fatemeh Moheimani, Sherry Y Wu, Anil K Sood, et al. (2015) Advances and Challenges of Liposome Assisted Drug Delivery. *Front*
20. Park John W (2002) Liposome-based drug delivery in breast cancer treatment. *Breast Cancer Research* 4(3): 95-99.
21. Silva JO, Fernandes RS, Lopes SC, Cardoso VN, Leite EA, et al. (2016) pH-sensitive, long-circulating liposomes as an alternative tool to deliver doxorubicin into tumors: A feasibility animal study. *Mol Imag Biol* 18(6): 898-904.
22. Karanth Hamsaraj, Murthy RS Rayasa (2007) pH-Sensitive liposomes-principle and application in cancer therapy. *J Pharm Pharmacol* 59(4): 469-483.
23. Ferreira DDS, Sávia CDAL, Marina SF, Mônica CO (2013) pH-sensitive liposomes for drug delivery in cancer treatment. *Therapeutic Delivery* 4(9): 1099-123.
24. Reja Rahi M, Mohsina Khan, Sumeet K Singh, Rajkumar Misra, Anjali Shiras, et al. (2016) pH sensitive coiled coils: a strategy for enhanced liposomal drug delivery. *Nanoscale* 8(9): 5139-5145.
25. Miyazaki M, Eiji Y, Hiroshi H, Atsushi H, Kenji K (2018) Hyaluronic Acid-Based pH-Sensitive Polymer-Modified Liposomes for Cell-Specific Intracellular Drug Delivery Systems. *Bioconjugate Chem* 29 (1): 44-55.
26. Li Wei, Feng SS, Guo Y (2012) Block copolymer micelles for nanomedicine. *Nanomedicine* 7(2): 169-172.
27. Hongliang Cao, Chao Chen, Debiao Xie, Xin Chen, Ping Wang, et al. (2018) A hyperbranched amphiphilic acetal polymer for pH-sensitive drug delivery. *Polym Chem (The Royal Society of Chemistry)* 9(2): 169-177.
28. Tang S, Meng Q, Sun H, Su J, Yin Q, et al. (2017) Dual pH-sensitive micelles with charge-switch for controlling cellular uptake and drug release to treat metastatic breast cancer. *Biomaterials* 114: 44-53.
29. Uthaman S, Kang Moo Huh, In-Kyu Park (2018) Tumor microenvironment-responsive nanoparticles for cancer theragnostic applications. *Biomater Res* 22: 22.
30. Yang Zhang Can, You QiangYang, Tu Xiong Huang, Bin Zhao, Xin Dong Guo, et al. (2012) Self-assembled pH-responsive MPEG-b-(PLA-co-PAE) block copolymer micelles for anticancer drug delivery. *Biomaterials* 33(26): 6273-6283.
31. Zhou X, Luo S, Tang R, Wang R, Wang J (2015) Diblock copolymers of polyethylene glycol and a polymethacrylamide with side-chains containing twin ortho ester rings: synthesis, characterization, and evaluation as potential pH-responsive micelles.

- Macromol. Biosci 15(3): 385-394.
32. Debele TA, Kuan-Yi Lee, Ning-Yu Hsu, Yi-Ting Chiang, Lu-Yi Yu, et al. (2017) A pH sensitive polymeric micelle for co-delivery of doxorubicin and α -TOS for colon cancer therapy. *J Mater Chem B* 5(29): 5870-5880.
33. Mozhi A, Israr A, Chukwunweike IO, Chan Li, and Xing JL (2017) pH-sensitive polymeric micelles for the Co-delivery of proapoptotic peptide and anticancer drug for synergistic cancer therapy. *Royal Soc Chem Advances Issue 7(21)*: 12886-12896.
34. Ma B, Zhuang W, Liu G, Wang Y (2018) A biomimetic and pH-sensitive polymeric micelle as carrier for paclitaxel delivery. *Regen Biomater* 5(1): 15-24.
35. Wang J, Lu Y, Li S, Wang X, Huang Y. et al. (2019) pH-sensitive amphiphilic triblock copolymers containing ortho ester main-chains as efficient drug delivery platforms. *Mater Sci Eng C Mater Biol Appl* 94: 169-178.
36. Somayyeh FIS, Mojtaba A, Mortaza M (2019) A novel gold nanorods-based pH-sensitive thiol-ended triblock copolymer for chemo-photothermo therapy of cancer cells. *Journal of Biomaterials Science, Polymer Edition* 30(1): 12-33.
37. Movassaghian S, Merkel OM, Torchilin VP (2015) Applications of polymer micelles for imaging and drug delivery. *Wiley Interdiscip Rev Nanomed Nanobiotechnol* 7(5): 691-707.
38. Ko Jinyoung, Kyeongsoon Park, Yoo-Shin Kim, Min Sang Kim (2007) Tumoral acidic extracellular pH targeting of pH-responsive MPEG-poly(β -amino ester) block copolymer micelles for cancer therapy. *Journal of Controlled Release* 123(2): 109-115.
39. Giacomelli Fernando C, Petr Stepánek, Cristiano Giacomelli, Vanessa Schmidt, Eliézer Jäger, et al. (2011) PH-triggered micelles based on a pH-responsive PDPA (poly[2-(diisopropylamino)ethyl methacrylate]) inner core and a PEO (poly(ethylene oxide)) outer shell as a potential tool for the cancer therapy. *Soft Matter* 7(19): 9316-9325.
40. Kim Dongin, Zhong Gao Gao, Eun Seong Lee, You Han Bae (2009) *In vivo* evaluation of doxorubicin-loaded polymeric micelles targeting folate receptors and early endosomal pH in drug-resistant ovarian cancer. *Mol Pharm* 6(5): 1353-1362.
41. Wang Jie, Gejing De, Qiaoxin Yue, Hai Ma, Jintang Cheng, et al. (2018) pH Responsive Polymer Micelles Enhances Inhibitory Efficacy on Metastasis of Murine Breast Cancer Cells. *Front Pharmacol* 9: 543.
42. Zhuang W, Ma B, Liu G, Chen X, Wang Y (2018) A fully absorbable biomimetic polymeric micelle loaded with cisplatin as drug carrier for cancer therapy. *Regen Biomater* 5(1): 1-8.
43. Zhou Xin Xin, Long Jin, Rui Qun Qi, Teng Ma (2018) pH-responsive polymeric micelles self-assembled from amphiphilic copolymer modified with lipid used as doxorubicin delivery carriers. *Royal Society open Sci* 5(3): 171654.
44. Das Aparesh N, Vishal Gupta DV, Gowda Rohit R Bhosale (2017) A Review on pH -Sensitive Polymeric Nanoparticles for Cancer Therapy. *International Journal of ChemTech Research* 10(6): 575-588.
45. Zhou Q, Zhang L, Yang T, Wu H (2018) Stimuli-responsive polymeric micelles for drug delivery and cancer therapy 13: 2921-2942.
46. Johnson RP, Saji Uthaman, Rimesh Augustine, Yu Zhang, Hua Jin, et al. (2017) Glutathione and endosomal pH-responsive hybrid vesicles fabricated by zwitterionic polymer block poly(L-aspartic acid) as a smart anticancer delivery platform. *React Funct Polym* 119: 47-56.
47. John JV, Uthaman S, Augustine R, Lekshmi KM, Park IK, Kim I (2017) Biomimetic pH/redox dual stimuli-responsive zwitterionic polymer block poly((L)-histidine) micelles for intracellular delivery of doxorubicin into tumor cells. *J Polym Sci Pol Chem* 55(12): 2061-2070.
48. Johnson RP, Uthaman S, John JV, Lee HR, Lee SJ, et al. (2015) Poly(PEG)-b-poly(L-lysine)-b-poly(L-histidine) hybrid vesicles for Tumoral pH-triggered intracellular delivery of doxorubicin hydrochloride. *ACS Appl Mater Inter* 7(39): 21770-21779.
49. Marques João G, Gaspar VM, Costa EC, Paquete CM (2013) Synthesis and characterization of micelles as carriers of non-steroidal anti-inflammatory drugs (NSAID) for application in breast cancer therapy. *Colloids and surfaces B: Biointerfaces* 113: 375-383.
50. Zhi Zeng, Zei Liang Wei, Li-Mei Ma, Yao Xu (2017) pH-responsive nanoparticles based on Ibuprofen prodrug as drug carriers for inhibition of primary tumor growth and metastasis. *J Mater Chem B* 5(33): 6860-6868.
51. Wei-liang Chen, Fang Li, Yan Tang, Shu-di Yang, Ji-zhao Li, et al. (2017) Stepwise pH-responsive nanoparticles for enhanced cellular uptake and on-demand intracellular release of doxorubicin 12: 4241-4256.
52. Biswas S, Kumari P, Lakhani PM, Ghosh B (2016) Recent

- advances in polymeric micelles for anti-cancer drug delivery. *Eur J Pharm Sci* 83: 184-202.
53. Ahmad Z, Tang ZH, Shah A, Lv SX, Zhang DW. et al. (2014) Cisplatin loaded methoxy poly (ethylene glycol)-block-poly (L-glutamic acid-co-L-phenylalanine) nanoparticles against human breast cancer cell. *Macromol Biosci* 14(9): 1337-1345.
 54. García-PB, Cristina PA, Alicia OR, Francisco S, Jose P. et al. (2019) Lipid-Based Nanoparticles: Application and Recent Advances in Cancer Treatment. *Nanomaterials* 9(4): 638.
 55. Tanbour R, Martins AM, Pitt WG, Husseini GA (2016). Drug delivery systems based on polymeric micelles and ultrasound: a review. *Curr Pharm Des* 22(19): 2796-2807.
 56. Jain S, Jain R, Das M, Agrawal AK, Thanki K, et al. (2014) Combinatorial bio-conjugation of gemcitabine and curcumin enables dual drug delivery with synergistic anticancer efficacy and reduced toxicity. *RSC Advances* 4(55): 29193-29201.
 57. Liao JH, Zheng H, Fei Z, Lu B, Zheng H, et al. (2018) Tumor-targeting and pH-responsive nanoparticles from hyaluronic acid for the enhanced delivery of doxorubicin. *Int J Biol Macromol* 113: 737-747.
 58. Cho K, Wang X, Nie S, Chen ZG, Shin DM (2008) Therapeutic nanoparticles for drug delivery in cancer. *Clin Cancer Res* 14(5): 1310-1316.
 59. Yandan Yao, Phei Er Saw, Yan Nie, Ping Pui Wong, Linjia Jiang, et al. (2018) Multifunctional sharp pH-responsive nanoparticles for targeted drug delivery and effective breast cancer therapy. *J Materials Chem B* 7(4): 576-585.
 60. Anajafi T, Mallik Sanku (2015) Polymersome-based drug-delivery strategies for cancer therapeutics. *Ther Deliv* 6(4): 521-534.
 61. Asano I, So S, Lodge TP (2016) Oil-in-oil emulsions stabilized by asymmetric polymersomes formed by AC + BC block polymer co-assembly. *J Am Chem Soc* 138(14): 4714-4717.
 62. Zhao Yi, Xiaoming Li, Zhao X, Yang Y, Li H, et al. (2017) Asymmetrical Polymer Vesicles for Drug delivery and Other Applications. *Front Pharmacol* 8: 374.
 63. Thambi Thavasyappan, Jae Hyung Park, Doo Sung Lee (2016) Stimuli-Responsive Polymersomes for Cancer Therapy. *Biomaterials Science* 4(1): 55-69.
 64. Anitha P, Bhargavi JG, Sravani B, Aruna, Ramkanth S (2018) Recent Progress of Dendrimers in Drug Delivery For Cancer Therapy. *Int J App Pharm* 10(5): 34-42.
 65. Castro RI, Oscar Forero-Doria, Luis Guzman (2018) Oscar Forero-Doria and Luis Guzman. Perspectives of Dendrimer-based Nanoparticles in Cancer Therapy. *Anais da Academia Brasileira de Ciências (Annals of the Brazilian Academy of Sciences)* 90 (2): 2331-2346.
 66. Ekladios Iriny, Yolonda L Colson, Mark WG (2019) Polymer-drug conjugate therapeutics: advances, insights and prospects. *Nature Reviews Drug Discovery* 18(4): 273-294.
 67. Wen S, Liu H, Cai H, Shen M, Shi X (2013) Targeted and pH-responsive delivery of doxorubicin to cancer cells using multifunctional dendrimer-modified multi-walled carbon nanotubes. *Adv Healthc Mater* 2(9): 1267-1276.
 68. Zhang Mengen, Jingyi Zhu, Yun Zheng, Rui Guo, Shige Wang, et al. (2018) Doxorubicin-Conjugated PAMAM Dendrimers for pH-Responsive Drug Release and Folic Acid-Targeted Cancer Therapy. *Pharmaceutics* 10(3): 162.
 69. Zhu J, Wang G, Alves CS, Tomás H, Xiong Z, et al. (2018) Multifunctional Dendrimer-Entrapped Gold Nanoparticles Conjugated with Doxorubicin for pH-Responsive Drug Delivery and Targeted Computed Tomography Imaging. *Langmuir* 34(41): 12428-12435.
 70. Yang Yihua, Zhe Wang, Ying Peng, Jinsong Ding, Wenhu Zhou (2019) A Smart pH-Sensitive Delivery System for Enhanced Anticancer Efficacy via Paclitaxel Endosomal Escape. *Front. Pharmacol* 10.
 71. Battistella Claudia, Harm-Anton Klok (2017) Controlling and Monitoring Intracellular Delivery of Anticancer Polymer Nanomedicines. *Macromol. Biosci* 17(10).
 72. Sirova Milada, Tomas Mrkvan, Tomas Etrych, Petr Chytil, Rossmann P, et al. (2009) Preclinical Evaluation of Linear HPMA-Doxorubicin Conjugates with pH-Sensitive Drug Release: Efficacy, Safety, and Immunomodulating Activity in Murine Model. *Pharmaceutical Research* 27(1): 200-208.
 73. Talelli Marina, Maryam Iman, Wim E Hennink, Amir K Varkouhi (2010) Core-crosslinked polymeric micelles with controlled release of covalently entrapped doxorubicin. *Biomaterials* 31(30): 7797-7804.
 74. Zhu S, Lansakara-P DS, Li X, Cui Z (2012) Lysosomal delivery of a lipophilic gemcitabine prodrug using novel acid-sensitive micelles improved its antitumor activity. *Bioconjug Chem* 23(5): 966-980.

75. Zhang M, Liu J, Kuang Y, Li Q, Zheng DW, et al. (2017) Ingenious pH-sensitive dextran/mesoporous silica nanoparticles based drug delivery systems for controlled intracellular drug release. *Int J Biol Macromol* 98: 691-700.
76. Etrych T, Subr V, Strohalm J, Sirová M, Rihová B, et al. (2012) HPMA copolymer-doxorubicin conjugates: the effects of molecular weight and architecture on biodistribution and in vivo activity. *J Control Release* 164(3): 346-354.
77. Peilan Qi, Xiaohe Wu, Lei Liu, Huimin Yu, Shiyong Song (2018) Hydrazone-Containing Triblock Copolymeric Micelles for pH-Controlled Drug Delivery. *Front Pharmacol* 9: 12.
78. Takahashi A, Yamamoto Y, Yasunaga M, Koga Y, Kuroda J, et al. (2013) NC-6300, an epirubicin-incorporating micelle, extends the antitumor effect and reduces the cardiotoxicity of epirubicin. *Cancer Sci* 104(7): 920-925.
79. Alani AWG, Younsoo Bae, Deepa A Rao, Glen S (2010) Kwon. Polymeric micelles for the pH-dependent controlled, continuous low dose release of Paclitaxel. *Biomaterials* 31(7): 1765-1772.
80. Yulong Jin, Yanyan H, Hua Y, Guoquan L, Rui Zhao (2015) A peptide-based pH-sensitive drug delivery system for targeted ablation of cancer cells. *Chem Communications* 77(51): 14454-14457.
81. Ulbrich K, Etrych T, Chytil P, Jelinkova M, Rihova B (2003) HPMA copolymers with pH-controlled release of doxorubicin: In vitro cytotoxicity and in vivo antitumor activity. *J Control Release* 87(1-3): 33-47.
82. Lavignac N, Johanna L Nicholls, Paolo Ferruti, Ruth Duncan (2009) Poly(amidoamine) Conjugates Containing Doxorubicin Bound via an Acid-Sensitive Linker. *Macromolecular Biosci* 9(5): 480-487.
83. Zhu S, Hong M, Tang G, Qian L, Lin J, et al. (2010) Partly PEGylated polyamidoamine dendrimer for tumor-selective targeting of doxorubicin: the effects of PEGylation degree and drug conjugation style. *Biomaterials* 31(6): 1360-1371.
84. Hu Q, Rijcken CJ, Bansal R, Hennink WE, Storm G, et al. (2015) Complete regression of breast tumour with a single dose of docetaxel-entrapped core-cross-linked polymeric micelles. *Biomaterials* 53: 370-378.
85. Thambi T, Deepagan VG, Yoo CK, Park JH (2011) Synthesis and physicochemical characterization of amphiphilic block copolymers bearing acid-sensitive orthoester linkage as the drug carrier. *Polymer* 52(21): 4753-4759.
86. Zha Q, Wang X, Cheng X, Fu SX, Yao WJ, et al. (2017) Acid degradable carboxymethyl chitosan nanogels via an ortho ester linkage mediated improved penetration and growth inhibition of 3-D tumor spheroids *in vitro*. *Mat Sci Eng C-Mater* 78: 246-257.
87. Belali S, Karimi AR, Hadizadeh M (2018) Cell-specific and pH-sensitive nanostructure hydrogel based on chitosan as a photosensitizer carrier for selective photodynamic therapy. *Int J Biol Macromol* 110: 437-48.
88. Tao YC, Liu SW, Zhang Y, Chi ZG, Xu JR (2018) A pH-responsive polymer based on dynamic imine bonds as a drug delivery material with pseudo target release behavior. *Polym Chem-Uk* 9(7): 878-884.
89. Popat A, Liu J, Lu GQ, Qiao SZ (2012) A pH-responsive drug delivery system based on chitosan coated mesoporous silica nanoparticles. *J Mater Chem* 22: 11173-11178.
90. Kang EB, Lee JE, Mazrad ZAI, In I, Jeong JH, et al. (2018) pH-responsive fluorescent carbon nanoparticles for tumor selective theranostics via pH turn on/off fluorescence and photothermal effect in vivo and in vitro. *Nanoscale* 10(5): 2512-2523.
91. Ray Sayoni, Zhao Li, Chao-Hsiung Hsu, Lian-Pin Hwang, Ying-Chih Lin, et al. (2018) Dendrimer- and copolymer-based nanoparticles for magnetic resonance cancer theranostics. *Theranostics* 8(22): 6322-6349.
92. Huang S, Ziyong Cheng, Yinyin Chen, Bei Liu, Xiaoran Deng, et al. (2015) Multifunctional polyelectrolyte multilayers coated onto Gd₂O₃:Yb³⁺,Er³⁺@MSNs can be used as drug carriers and imaging agents. *RSC Advances* 52.
93. Tian S, Liu G, Wang X, Zhang G, Hu J (2016) pH-Responsive Tumor-Targetable Theranostic Nanovectors Based on Core Crosslinked (CCL) Micelles with Fluorescence and Magnetic Resonance (MR) Dual Imaging Modalities and Drug Delivery Performance. *Polymers (Basel)* 8(6): pii: E226.
94. Yu Shufang, Guolin Wu, Xin Gu, Jingjing Wang, et al. (2013) Magnetic and pH-sensitive nanoparticles for antitumor drug delivery. *Colloids and Surfaces B: Biointerfaces* 103: 15-22.
95. Wang Jingjing, Chu Gong, Yinong Wang, Guolin Wu (2014) Magnetic and pH sensitive drug delivery system through NCA chemistry for tumor targeting. *Royal Society of Chemistry Advances* 31.

96. Karimi Z, Abbasi S, Shokrollahi H, Yousefi G, Fahham M, et al. (2017) Pegylated and amphiphilic Chitosan coated manganese ferrite nanoparticles for pH-sensitive delivery of methotrexate: Synthesis and characterization. *Mater Sci Eng* 71: 504-511.
97. Wu Juan, Aipeng Deng, Wei Jiang, Renbing Tian, Shen Y (2017) Synthesis and *in vitro* evaluation of pH-sensitive magnetic nanocomposites as methotrexate delivery system for targeted cancer therapy. *Materials Science & engineering C, Materials for Biological Applications* 71: 132-140.
98. Sun X, Du R, Zhang L, Zhang G, Zheng X. et al. (2017) A pH-Responsive Yolk-Like Nanoplatfor for Tumor Targeted Dual-Mode Magnetic Resonance Imaging and Chemotherapy. *ACS Nano* 11(7): 7049-7059.
99. Wang Xin, Ziyu Gao, Long Zhang, Huiming Wang, Xiaohong Hu (2018) A Magnetic and pH-Sensitive Composite Nanoparticle for Drug Delivery. *Nanomater* 2018: 7.
100. Lungu II, Rădulescu M, Mogoșanu GD, Grumezescu AM (2016) pH sensitive core-shell magnetic nanoparticles for targeted drug delivery in cancer therapy. *Rom J Morphol Embryol* 57(1): 23-32.
101. Bardajee GR, Hooshyar Z, Farsi M, Mobini A, Sang G (2016) Synthesis of a novel thermo/pH sensitive nanogel based on salep modified graphene oxide for drug release. *Mater Biol Appl* 72: 558-565.
102. Yadav HKS, Al Halabi NA, Alsalloum GA (2017) Nanogels as Novel Drug Delivery Systems - A Review. *J Pharm Pharm Res* 1: 5.
103. Garg T, Arora S, Murthy R, Goyal AK (2012). Development, optimization & evaluation of porous chitosan scaffold formulation of gliclazide for the treatment of type-2 diabetes mellitus. *Drug Deliv Lett.* 2(4): 251-261.
104. Sharma A, Tarun Garg, Amrinder Aman, Kushan Panchal, Rajiv Sharma, et al. (2016) Nanogel-an advanced drug delivery tool: Current and future. *Artif Cells, Nanomed Biotechnol* 44(1): 165-177.
105. Oishi M, Hisato Hayashi, Michihiro Iijima, Yukio Nagasaki (2007) Endosomal release and intracellular delivery of anticancer drugs using pH-sensitive PEGylated nanogels. *J Mater Chem* 17(35): 3720-3725.
106. Liu K, Zheng D, Zhao J, Tao Y, Yingsa W, et al. (2018) pH-Sensitive nanogels based on the electrostatic self-assembly of radionuclide ¹³¹I labelled albumin and carboxymethyl cellulose for synergistic combined chemo-radioisotope therapy of cancer. *J Mater Chem B* 29(6): 4738-4746.
107. Taghizadeh B, Shahrouz T, Seyed AM, Zoha SM, Karim D, et al. (2015) Classification of stimuli-responsive polymers as anticancer drug delivery systems. *Drug Deliv* 22(2): 145-155.
108. Wei P, Gangapurwala G, Pretzel D, Leiske MN, Wang L (2018) Smart pH-sensitive Nanogels for Controlled Release in Acidic Environment. *Biomacromolecules* 20(1): 130-140.
109. Urban-Klein B, Werth S, Abuharbeid S, Czubayko F, Aigner A (2005) RNAi-mediated gene-targeting through systemic application of polyethylenimine (PEI)-complexed siRNA in vivo. *Gene Ther* 12(5): 461-466.
110. Lee ES, Gao Z, Kim D, Park K, Kwon IC, et al. (2008) Super pH sensitive multifunctional polymeric micelle for tumor pH(e) specific TAT exposure and multidrug resistance. *J Control Release* 129(3): 228-236.
111. Rao NV, Mane S, Kishore A, Das Sarma J, Shunmugam R (2011) Norbornene derived doxorubicin copolymers as drug carriers with pH responsive hydrazone linker. *Biomacromolecules* 13(1): 221-230.
112. Wei H, Zhuo RX, Zhang XZ (2013) Design and development of polymeric micelles with cleavable links for intracellular drug delivery. *Prog Polym Sci* 38(3-4): 503-535.
113. Liu M, Du H, Zhang W, Zhai G (2017) Internal stimuli-responsive nanocarriers for drug delivery: design strategies and applications. *Mater Sci Eng C* 71: 1267-1280.
114. Shih Y, Venault A, Tayo LL, Chen SH, Higuchi A, et al. (2017) A Zwitterionic-shielded carrier with pH-modulated reversible self assembly for gene transfection. *Langmuir* 33: 1914-1926.
115. Shen Y, Huadong Tang, Maciej Radosz, Edward Van Kirk (2008) pH-Responsive Nanoparticles for Cancer Drug Delivery. *Methods in Molecular Biology* 437: 183-216.
116. Weiwei Gao, Juliana M Chan, Omid C Farokhzad (2010) pH Responsive nanoparticles for drug delivery. *Mol. Pharmaceutics* 7(6): 1913-1920.
117. Liu J, Huang Y, Kumar A, Tan A, Jin S, et al. (2014) pH-sensitive nano-systems for drug delivery in cancer therapy. *Biotechnol adv* 32(4): 693-710.